

Technical Data Sheet

Date of Issue 21/01/2018

Rev. 06_12/02/2024

3008

Entry Level Body Shop Masking Tape

**Product Description**

Entry Level Body Shop, temperature resistant masking tape characterized by a semi crepe paper backing and a solvent borne rubber resin adhesive. Suitable for non – critical spray painting activities at moderate temperature up to 60°C /140°F (1 hour). It performs in overlapping the tape, with masking paper and masking film with good holding power. Used as premium grade product in building industry as well. FSC® and PEFC certified masking tapes available on demand.

Features

- Medium adhesion
- Good holding power
- Clean removal after drying cycle at 60°C/140°F (max. 1 hour)
- Consistent adhesion on painted metal, rubber and glass
- Quick stick
- Good paint anchorage

Main Applications

- Professional masking for high temperature spray painting in Car Repairing industry.

Technical Data

	Metric	Imperial Units	Test Method
Total weight*	90 g/m ²	90 g/m ²	ISO 536
Total thickness*	120 µm	4.7 mils	Internal
MD tensile strength*	38 N/cm	21.7 Lbs/in	AFERA 5004/PSTC 131
MD elongation at break*	7 %	7 %	AFERA 5004/PSTC 131
Adhesion to steel plate*	2.1 N/cm	19.2 oz/in	AFERA 5001/PSTC 101
Service temperature up to (1 hour)	60°C	140°F	

Backing material

Saturated crepe paper

Type of adhesive

Natural rubber

*Typical value

Available colour

White Yellow Brown

Technical Information and Product Use

All technical information and data above mentioned are provided to the best of our knowledge on the basis of our practical experience. Figures shown refer to average values only, based on tests carried out in conditioned laboratory and are not valid for specification. The company reserves the right to modify or change the products at any time without notice. The accuracy or completeness of such information is not guaranteed. The technical information, suggestions and other statements contained in this document have been compiled for your guidance and usage. PPM Industries reminds the user of the products to make sure that the product is used as per the instructions and suggestions provided. It is the user's sole responsibility to determine the suitability of the product in actual application under specific conditions.

Storage and Shelf Life

Suggested storage in dry area away from direct sunlight temperature should range from 59°F / 15°C to 77°F / 25°C with max relative humidity of 50%. Tape and jumbo roll should be used respectively within 12 months and 6 months from date of shipment. PPM Industries does not take responsibility for the defective material if is not stored and used in accordance with the conditions listed above.